

MC226 FKM 90 Shore Brown

ASTM D 2000 M2 HK 910 A1-10 B37

Material Datasheet • Issue 2 • Dec 2017

Material

FKM 90 Shore Brown
ASTM D 2000 M2 HK 910 A1-10 B37

Description

- Low compression set FKM O Ring grade
- Copolymer with 66% fluorine content
- Cure system is Bisphenol

Application

This material has excellent resistance to oils, fuels, lubricants, most mineral acids, aliphatic and aromatic hydrocarbons.

Temperature

- Low temperature service limit -4°F (-20°C)
- Upper temperature continuous service limit +400°F (+204°C).

Products

- Extrusions (cords/profiles/tubes)
- Mouldings (Custom/O Rings)
- VulcOrings



Physical Properties

Original	Standard	Typical Values
Specific Gravity	ASTM D1817	2.51
Durometer shore A (slab)	ASTM D2240	87
Elongation % (Dumbbell)	ASTM D412	129.3
Tensile strength Psi (MPa) (Dumbbell)	ASTM D412	1618 (11.15)
Compression set % 22h @ 347°F (175°C) (slab)	ASTM D395B	9.42
Low temperature TR-10°F (°C)*	ASTM D1329	-17

* Nominal value based on a typical 75 shore vulcanizate

Heat Ageing 70h @ 482°F (250°C) ASTM D573

Durometer change points shore A	+2.6
Elongation change %	-20
Tensile strength change Psi (MPa)	+392 (27)
Weight loss grams	0.17

Fluid Immersion Oil No 3 70h @ 302°F (150°C) ASTM D471

Volume change %	+2.34
Durometer change points shore A	+1.7
Elongation change %	+1.15
Tensile strength change Psi (MPa)	-638 (4.4)

Information

The above information corresponds to our current knowledge and is offered solely to provide possible suggestions for your own experimentations. It is not intended to substitute any testing you may need to conduct to determine suitability of our products for your end use. Northern Engineering reserves the right to revise this information as new knowledge and experience becomes available. Northern Engineering makes no warranties and assumes no liability in connection with any use of the above information.

