

MC235 Epdm 80 Shore

ASTM D 2000 M6CA 710 A25 B35 C32

Material Datasheet • Issue 3 • Mar 2018

Material

Epdm 80 Shore

ASTM D 2000 M6CA 710 A25 B35 C32

Description

- Epdm is a polymer of ethylene, propylene and a small amount of diene
- Cure system is peroxide

Application

Epdm's have a good resistance to ozone, ageing and weathering. They are suitable for HFC & HFD flame retardant hydraulic oils and brake fluids and have exceptional resistance to hot water, steam and acids.

Temperature

- Low temperature service limit -40°F (-40°C)
- Upper temperature continuous service limit +284°F (+140°C)

Products

- Encapsulated O Rings
- Mouldings (custom/O Rings)



Physical Properties

Original	Standard	Typical Values
Specific Gravity	ASTM D1817	1.10
Durometer shore A (slab)	ASTM D2240	79
Elongation % (Dumbbell)	ASTM D412	273
Tensile strength Psi (MPa) (Dumbbell)	ASTM D412	2320 (16)
Compression set % 22h @ 212°F (100°C) (slab)	ASTM D395B	7.8

Heat Ageing 70h @ 258°F (125°C) ASTM D573

Durometer change points shore A	-0.5
Elongation change %	-6.8
Tensile strength change Psi (MPa)	+94 (+0.65)
Weight loss grams	0.01

Fluid Immersion Oil No 3 70h @ 302°F (150°C) ASTM D471

Volume change %	+110
Durometer change points shore A	-30
Elongation change %	-47
Tensile strength change Psi (MPa)	-136 (-9.4)

Information

The above information corresponds to our current knowledge and is offered solely to provide possible suggestions for your own experimentations. It is not intended to substitute any testing you may need to conduct to determine suitability of our products for your end use. Northern Engineering reserves the right to revise this information as new knowledge and experience becomes available. Northern Engineering makes no warranties and assumes no liability in connection with any use of the above information.

