

MATERIAL	EPDM 95 Shore Metal/X-Ray Detectable FDA Blue ASTM D 2000 M2CA 910 A25
DESCRIPTION	EPDM is a polymer of ethylene, propylene and a small amount of diene Cure system is peroxide FDA compliant to CFR 21 177-2600
APPLICATION	EPDM's have good resistance to ozone, ageing and weathering. They are suitable for HFC & HFD flame retardant hydraulic oils and brake fluids and have exceptional resistance to hot water, steam and acids. This compound can be detected by metal detectors and X-Ray detectors.
TEMPERATURE	Low temperature service limit -40°F (-40°C) Upper temperature continuous service limit +284°F (+140°C)
PRODUCTS	Moulding (custom/O rings)

PHYSICAL PROPERTIES

ORIGINAL	STANDARD	TYPICAL VALUES
Specific Gravity	ASTM D1817	1.32
Durometer shore A (slab)	ASTM D2240	94
Elongation % (Dumbbell)	ASTM D412	158
Tensile strength Psi (Mpa) (Dumbbell)	ASTM D412	1639 (11.3)
Compression set % 22h @ 158°F (70°C) (slab)	ASTM D395B	19.0
HEAT AGEING 70h @ 212°F (100°C) ASTM D573		
Durometer change points shore A		+2
Elongation change %		-67
Tensile strength change Psi (Mpa)		-421 (-2.9)
Weight loss %		1.3

Information

The above information corresponds to our current knowledge and is offered solely to provide possible suggestions for your own experimentations. It is not intended to substitute any testing you may need to conduct to determine suitability of our products for your end use. Northern Engineering reserves the right to revise this information as new knowledge and experience becomes available. Northern Engineering makes no warranties and assumes no liability in connection with any use of the above information.