

MATERIAL	Nitrile 65 Shore Metal/X-Ray Detectable FDA Blue ASTM D 2000 M2BG 610 B14 E034
DESCRIPTION	NBR Acrylonitrile-Butadiene-Rubber ACN content is 33% Cure system is sulphur FDA compliant to CFR 21 177-2600 & European regulations EC1935/2004
APPLICATION	This material has an excellent resistance aliphatic, hydrocarbons (e.g. propane, butane and petroleum), mineral oils/greases, vegetable/animal oils/greases, heating oil and diesel fuel. This compound can be detected by metal detectors and X-Ray detectors.
TEMPERATURE	Low temperature service limit -22°F (-30°C) Upper temperature continuous service limit +248°F (+120°C)
PRODUCTS	Extrusions (cords/profiles/tubes) Hot Vulcanised O rings & Profiles Moulding (custom/O rings)

PHYSICAL PROPERTIES

ORIGINAL	STANDARD	TYPICAL VALUES
Specific Gravity	ASTM D1817	1.48
Durometer shore A (slab)	ASTM D2240	61
Elongation % (Dumbbell)	ASTM D412	664
Tensile strength Psi (Mpa) (Dumbbell)	ASTM D412	1218 (8.4)
Compression set % 22h @ 158°F (70°C) (slab)	ASTM D395B	29.2
HEAT AGEING 70h @ 212°F (100°C) ASTM D573		
Durometer change points shore A		+5
Elongation change %		-179
Tensile strength change Psi (Mpa)		-290 (-2.0)
Weight loss %		1.6
FLUID IMMERSION Oil No 3 70h @ 212°F (100°C) ASTM D471		
Volume change %		+11.9
Durometer change points shore A		-11
Elongation change %		-130
Tensile strength change Psi (Mpa)		-232 (-1.6)

Information

The above information corresponds to our current knowledge and is offered solely to provide possible suggestions for your own experimentations. It is not intended to substitute any testing you may need to conduct to determine suitability of our products for your end use. Northern Engineering reserves the right to revise this information as new knowledge and experience becomes available. Northern Engineering makes no warranties and assumes no liability in connection with any use of the above information.