



MATERIAL Silicone 70 Shore Grey

DESCRIPTION Extrusion grade formulated to meet FAR 25.853

APPLICATION This material has excellent thermal resistance to both high and low temperatures and is good with oxygen and ozone attack.

TEMPERATURE Low temperature service limit -76°F (-60°C)
Upper temperature continuous service limit +446°F (+230°C)

PRODUCTS Extrusions (cords/profiles/tubes)
Hot Vulcanised O rings & Profiles

PHYSICAL PROPERTIES

ORIGINAL	STANDARD	TYPICAL VALUES
Specific Gravity	BS ISO 2781:2008 + A1 : 2012	1.39
Durometer IRHD	BS ISO 48:2010	70
Elongation at break (%)	BS ISO 37:2011 (E)	530
Tensile strength (Mpa)	BS ISO 37:2011 (E)	7.2
Tear (N/mm)	BS ISO 34-1:2010 (E) - Method C	35

Information

The above information corresponds to our current knowledge and is offered solely to provide possible suggestions for your own experimentations. It is not intended to substitute any testing you may need to conduct to determine suitability of our products for your end use. Northern Engineering reserves the right to revise this information as new knowledge and experience becomes available. Northern Engineering makes no warranties and assumes no liability in connection with any use of the above information.